

# MC-201

## Metal & Roofing Sealant

### DESCRIPTION:

**x'traseal®** MC-201 metal & roofing sealant is one part sealant that offer excellent adhesion, outstanding durability and excellent gunnability for general sealing application.

### FEATURES:

- ◆ Outstanding durability
- ◆ One part no mixing
- ◆ Low voc (volatile organic compound)
- ◆ Surface will skin and dry, but the underneath will remain flexible.
- ◆ Flexible ( $\pm 3\%$ )
- ◆ Excellent gunnability (-20°C TO 50°C)
- ◆ Weather proof
- ◆ Low shrinkage
- ◆ No sagging
- ◆ Primerless adhesion to most materials
- ◆ Paintable after cured

### USES:

General joint sealing in external walling, window and door frames, roofs and others.

**WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS**

### NOT RECOMMENDED FOR:

MC-201 metal & roofing sealant is not suitable for high joint movement substrate (more than  $\pm 3\%$  joint movement).

### COLOUR:

White, grey and black. Other colours are available upon request

### APPLICATION:

- ◆ Surface must be clean and dry.
- ◆ Mask smooth surface to simplify clean up.
- ◆ Use approved back-up material in joint.
- ◆ Cut nozzle to desired size.
- ◆ Insert cartridge into caulking gun.
- ◆ Push sealant ahead for uniform bead.
- ◆ Tool within 10 minutes.
- ◆ Clean off excess sealant with mineral spirit.

### CURING TIME:

MC-201 metal & roofing sealant will tack free in approximately 24 hours.

### SPECIFICATION:

Curing System	Oxidizing
Appearance	Non-Sagging Paste
Odour	Oleo-Resinous
Specific Gravity	1.60 $\pm$ 0.3
Max.Joint Movement	$\pm$ 3%
Shrinkage	5 % Approx.
Tack Free Time	24 Hours Approx.
Application Temp.	4°C To 50°C
Service Temp.	-5°C To 60°C
Shelf Life	12 Months

### STORAGE:

Material should be stored in a dry and cool place between +5°C TO +30°C.

### CAUTION:

Read and understand material safety data sheet of this product before handling or using.

*This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.*

